

## Product Data Sheet

### Barrikade PU-SLF 2K Komfort StoPur SL 525

# Barrikade®

Self-leveling flooring

#### Product description:

**Barrikade PU-SLF 2K Komfort** is a solvent free, self-leveling, flexible and decorative pigmented polyurethane flooring, and gives a comfortable surface. Comes in several colours.

#### Areas of use:

**Barrikade PU-SLF 2K Komfort** is used indoors in such areas as offices, hospitals, schools, shopping centres or other areas indoors where a comfortable and decorative floor is valued. Intended for light to medium loadings.

#### Mixing:

Component B is added to component A and mixed well with a low speed drill for 3 min.

**Barrikade PU-SLF 2K Komfort** is delivered in complete sets, with correct mixing ratio.

Store both components in room temperature at least one day before use.

#### Application:

**Barrikade PU-SLF 2K Komfort** is applied with a påføres med en tannet sparkel. Gå over med piggrulle for å fjerne eventuelle luftblærer som oppstår på overflaten. Åpnet forpakning har begrenset levetid.

Påføringsforhold: 12-30 °C og maks 70% relativ luftfuktighet.

Forbruk: 2,8-3,0 kg/m<sup>2</sup> pr. 1,5 mm beleg

#### Rengjøring:

Hender renses med rengjøringskrem og vaskes deretter med vanlig såpe og lunkent vann. Verktøy rengjøres med løsemiddel som f.eks. **Barrikade EP-Tynner**, aceton, xylene etc. Herdet materiale må fjernes mekanisk.

#### Vernetiltak:

Det skal benyttes hansker, egnet arbeidstøy og briller ved arbeider med fler-komponent herdeplaster.

Får man stoffet i øynene, skyll straks med store mengder vann og kontakt lege umiddelbart.

Se HMS produktdatablad!

#### Technical specifications:

<b>Product:</b>	Two-component, polyurethane
<b>Density [g/cm<sup>3</sup>]:</b>	1,8 (A+B); 1,9 (A); 1,2 (B)
<b>Volume solids:</b>	100 %
<b>Viscosity:</b>	
<b>Colour:</b>	See colour chart or contact supplier.
<b>Gloss:</b>	Glossy
<b>Mixing ratio:</b>	A : B = 6,9 : 1 (weight) A : B = 4,4 : 1 (volume)
<b>Pot-lfie:</b>	40 min at 20°C
<b>Application temperature:</b>	Temperature in the surface and air should be at least 12 °C.
<b>Drying time (23°C):</b>	Dust dry after 5-6 hours. Foot traffic after 10-12 hours. Maximum abrasion – and chemical resistance is achieved after 7 days.
<b>Shore A/D hardness after 3 days (23°C):</b>	85 / 40
<b>Shelf life:</b>	12 months in unopened container. Store dry and above freezing point. (5 – 25°C)

*De angitte data, produktenes egenskaper og våre anvisninger er basert på resultater fra egne og eksterne laboratorieforsøk, feltforsøk og praktiske erfaringer. Da den praktiske bruk ligger utenfor vår kontroll, kan vi ikke påta oss ansvar for det ferdige resultatet med mindre eventuelle mangler kan tilbakeføres direkte til mangler ved produktene. Eventuelt ansvar er begrenset oppad til produktenes kostnad.*

Product Data Sheet

---

**Barrikade PU-SLF 2K Komfort**

Barrikade®

Self-leveling flooring

StoCretec Flooring AS,  
Værftsgt. 7 A, N-1510 Moss,  
Tel. 69 27 30 00 - Fax. 69 27 46 30  
E-post: [stocretec.no@sto.com](mailto:stocretec.no@sto.com)  
[www.stocretec.no](http://www.stocretec.no)